



## Description

Gripset Patch-Phalt is a unique pothole and road solution to repair asphalt surfaces that have been affected by holes, cracking, breakup or general damage. Enhanced with polymerised technology Patch-Phalt strengthens and stabilises the repaired surface and assists in maintaining against future pavement breakdown.

As a safe alternative to hot asphalt repairs, Patch-Phalt requires no heating or bulky machinery making it highly portable and user friendly. It requires no priming to activate adhesion to repairs sections and can even be applied to potholes containing water, preventing downtime in wet weather conditions.

Patch-Phalt withstands immediate pedestrian and vehicular traffic after straight application for fast effective repairs.

## Features & Benefits

- Pre-mixed, ready to use
- Fast, effective permanent repair to asphalt surfaces
- No primer required
- Able for use in potholes containing water
- Can be exposed to traffic immediately after application
- Safe to use – no heating or hazardous odours emitted
- Excellent workability
- Does not bleed – no solvent bitumen residue will rise to the surface

## Uses

- Pothole repairs
- Car parks and driveway repairs
- Utility cuts
- Trip hazards and broken pavements
- Footpaths, speed humps and trenches
- Pole reinstatements
- Kerbs and channels
- Bridge work
- Overlays and edge repairs
- Can be compacted and overlaid with asphalt or left exposed

## Application

### Step 1: Surface Preparation

Remove all loose stone or debris by raking or sweeping the area to be filled. Check the perimeter areas of the pothole for any broken asphalt, removing any unstable material



### Step 2: Filling the pothole

Fill the pothole with Patch-Phalt, if needed a shovel or rake can be used to spread the material into the hole. It is best applied by compacting depths of a maximum of 50mm at a time. If the areas to be filled are deeper than 50mm, apply and compact in layers of maximum 50mm to obtain best result.



### Step 3: Compact

Using a compacting tool, e.g. flat pressing compactor, asphalt hand rammer or vibrating plate, pack the material in place ensuring the material is firmly compacted into the area. The better the compaction the faster the curing time. Ensure the material is well pressed and thoroughly compacted, forming an even solid surface. **Once these 3 simple steps are followed the area is ready for traffic.**



## Coverage

- 20kg of Gripset Betta Patch-Phalt will cover 0.5m<sup>2</sup> for areas consisting of 25mm compaction.

## Clean up

- For best results, brush white spirit or mineral turpentine onto affected area (as required) until removed.

## Storage conditions

- Best stored at room temperature
- Avoid cold freezing conditions and keep off concrete floors
- Shelf life is 12 months after opening
- Available in 20kg pails

## Note

- If the areas to be filled are deeper than 50mm, apply and compact in layers of maximum 50mm to obtain best result
- To loosen product and increase workability, Patch-Phalt can be activated by UV light or a warm source for 5-10 minutes.

## Gripset Betta Pty Ltd

ABN: 97 142 661 872

Telephone: TOLL FREE AUS: 13000 BETTA, NZ: 0800 474 7738

Email: [info@gripset.com](mailto:info@gripset.com)

Website: [www.gripsetbetta.com](http://www.gripsetbetta.com)

## Product Disclaimer

This product Information sheet summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this information sheet carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Gripset Betta Pty Ltd does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.

## Distributor Cyprus: M. A. Total Build Ltd

149 Arch. Makarios III Avenue, 3021 Limassol, Cyprus

Email: [info@totalbuild.com.cy](mailto:info@totalbuild.com.cy)

Tel: +357 99 121841, Fax: +357 25 381403

